

IN THE CLAIMS

1-7. (Cancelled)

8. (Currently amended) A replication method for producing a smooth object (18, 20) having a low surface roughness, comprising the steps of:

producing a replication master (10) by:

forming said master (10) such as to have a desired external surface shape

which at least partially corresponds to a counterform of a surface of an object (18, 20) to be produced by replication;

treating said external surface of said master (10) to obtain a predetermined surface roughness value; and

coating at least a part of said master (10) with a smoothing layer (16) made of a soluble polymer material having a flowability such that the top surface of said smoothing layer displays a smaller roughness than the surface on which it is formed;

coating at least a part of said smoothing layer (16) on said master (10) with an object material such that the surface of said object (18, 20) corresponds to a counterform of said master (10); and

releasing said object (18, 20) from said master (10).

9. (Currently amended) The method according to claim 8, wherein said releasing step comprises dissolving at least one of said smoothing layer (16) and ~~said a~~ release layer on top of said master (10) by a solvent.

10. (Previously presented) The method according to claim 8, which furthermore comprises the step of providing glue (20) to at least one of said object (18, 20) and an object support (12) and gluing them together before executing said releasing step.

11. (Previously presented) The method according to claim 10, wherein the amount of said glue (20) is chosen such as to fill gaps between said object (18, 20) and said object support (12).

12. (Currently amended) The method according to claim 8, wherein said object (18) is ~~an optical device (18), e.g.~~ a reflection or transmission monolayer, bilayer or multilayer.

13. (Previously presented) The method according to claim 12, which furthermore comprises the step of characterizing said optical device (18) on top of said master (10) before executing said releasing step.

14. (Previously presented) The method according to claim 13, wherein said characterization step comprises performing a profilometry or reflectometry measurement of said optical device (18).

15. (Previously presented) The method according to claim 8, wherein said object (20) is a substrate (20a) for an optical device (18).

16. (Previously presented) The method according to claim 15 and claim 10, wherein said object material and the material of said glue (20) are identical.

17. (Previously presented) The method according to claim 16, wherein said object material and said glue (20) comprise epoxy resin.

18. (Currently amended) The method according to claim 15, which furthermore comprises the step of coating at least a part of said master (10) with a protection layer on top of said smoothing layer (16) or on top of a release layer before applying said object material.

19-29. (Cancelled)

30. (New) The method according to claim 8, wherein said smoothing layer (16) is applied by dip-coating or spin-coating said master (10) with a liquid smoothing material and hardening said smoothing material.

31. (New) The method according to claim 8, which furthermore comprises the step of coating at least one additional smoothening layer on top of or under said soluble smoothening layer (16).

32. (New) The method according to claim 20, wherein at least one of said additional smoothening layers is made of a non-soluble material.

33. (New) The method according to claim 20, which furthermore comprises the step of coating a thin spacer layer between at least two adjacent smoothening layers.

34. (New) The method according to claim 33, wherein the thin spacer layer is a thin metallic spacer layer.

35. (New) The method according to claim 8, wherein the smoothening layer (16) has a roughness of 5 Angströms or less.